
TECHNICAL CHARACTERISTICS

MDi |  SILMM

BUSH-HAMMERED FINISH

Technical properties of Inalco's **MDi**


Dry-pressed slabs with a water absorption of less than 0.5%

GROUP Bla, Appendix G

ISO 13006, UNE-EN 14411

Finish	Bush-hammered
Thickness and sizes	10.5 mm 100 x 100 cm 6 mm 150 x 320 cm R / 150 x 150 cm / 100 x 250 cm / 100 x 100 cm

TECHNICAL CHARACTERISTICS AS PER APPLICABLE STANDARD:	Reference standard	Required value	Obtained mean value*
---	--------------------	----------------	----------------------

PHYSICAL CHARACTERISTICS			
Water absorption	EN-ISO 10545-3	E ≤ 0.5%	E ≤ 0.5%
Bending strength (N/mm²)	EN-ISO 10545-4	> 35 N / mm ²	Surpasses required value
Breaking strength (N)	EN-ISO 10545-4	Standard Thickness > 1,300 N	Surpasses required value
		 > 700 N	
Resistance to deep abrasion	EN-ISO 10545-6	≤ 175 mm ³	≤ 135 mm ³
Linear thermal expansion	EN-ISO 10545-8	Method available	≤ 9x10 ⁻⁶ K ⁻¹
Thermal shock resistance	EN-ISO 10545-9	Method available	Resistant
Frost resistance	EN-ISO 10545-12	Required	Resistant
Crazing resistance	EN-ISO 10545-11	Required	Resistant

CHEMICAL CHARACTERISTICS			
Resistance to low concentrations of acids and alkalis	EN-ISO 10545-13	As indicated by manufacturer	Resistant (LA)
Resistance to household cleaning products and swimming pool additives	EN-ISO 10545-13	Min. B	Resistant (A)
Resistance to staining	EN-ISO 10545-14	Min. Class 3	Class 5

DIMENSIONAL CHARACTERISTICS: PERMISSIBLE DEVIATION FROM WORK SIZE			
Length and width	EN-ISO 10545-2	±0.6% / ±2.0 mm	±0.6% / ±2.0 mm
Thickness	EN-ISO 10545-2	±5% / ±0.5 mm	±5% / ±0.5 mm
Straightness of sides	EN-ISO 10545-2	±0.5% / ±1.5 mm	±0.5% / ±1.5 mm
Squareness	EN-ISO 10545-2	±0.6% / ±2.0 mm	±0.6% / ±2.0 mm
Surface flatness	EN-ISO 10545-2	±0.6% / ±2.0 mm	±0.6% / ±0.5 mm
Surface appearance	EN-ISO 10545-2	Min. 95% of slabs without defects	Min. 95% of slabs without defects

*Results obtained from test samples.

Technical properties of Inalco's **MDi**

Dry-pressed slabs with a water absorption of less than 0.5%

GROUP Bla, Appendix G

ISO 13006, UNE-EN 14411

Finish	Bush-hammered
Thickness and sizes	10.5 mm 100 x 100 cm 6 mm 150 x 320 cm R / 150 x 150 cm / 100 x 250 cm / 100 x 100 cm

TECHNICAL CHARACTERISTICS AS PER APPLICABLE STANDARD:	Reference standard	Required value	Obtained mean value*
---	--------------------	----------------	----------------------

REACTION TO FIRE			
Reaction to fire of construction products and building elements	EN 13051	As indicated by manufacturer	A1 - A1 _{FL}
Flame spread rating	ASTM E-84	As indicated by manufacturer	Class I - A

TECHNICAL CHARACTERISTICS OF NON-SLIP PRODUCTS			
Technical characteristics of non-slip products	UNE-ENV 41901:2017	-----	Class 2
	ASTM - C 1028	-----	> 0.6
	DCOF: ANSI A 137.1:2012	-----	> 0.42
	DIN 51130	-----	R10
	DIN 51097	-----	A+B

* Results obtained from test samples.



INDUSTRIAS ALCORENSES CONFEDERADAS S.A.

C/ San Salvador, 54

12110, Alcora, Castellón (Spain)

(+34) 964 368 000

www.inalco.es www.inalcotrends.com



Publication date: July 2021